



HAL
open science

ENHANCED ARCING AS A FUNCTION OF ORGANIC EXPOSURE AND ARC CURRENT Pd AND Pd/Ag ELECTRODES

E. Gray, J.R. Pharney

► **To cite this version:**

E. Gray, J.R. Pharney. ENHANCED ARCING AS A FUNCTION OF ORGANIC EXPOSURE AND ARC CURRENT Pd AND Pd/Ag ELECTRODES. *Journal de Physique Colloques*, 1979, 40 (C7), pp.C7-267-C7-267. 10.1051/jphyscol:19797131 . jpa-00219104

HAL Id: jpa-00219104

<https://hal.science/jpa-00219104>

Submitted on 4 Feb 2008

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

**ENHANCED ARCING AS A FUNCTION OF ORGANIC EXPOSURE AND ARC CURRENT
Pd AND Pd/Ag ELECTRODES**

E.W. Gray and J.R. Pharney.

Bell Telephone Laboratories Columbus, Ohio 43213.

ABSTRACT

We report the existence of a region within which enhanced arcing (activation) exists for palladium and palladium/silver contacts, as a function of arc current and of exposure to organic vapors. The current range where activation exists is from ~0.1 to ~1.2 A, where the range of exposures (partial pressure times time) used for diethyl phthalate was from $\sim 10^{-3}$ to ~ 10 Pa s. At very low organic exposure levels (depending upon the organic vapor and the electrode metal), arc duration statistics show an exponential behavior. Under moderate to high organic exposure levels, arc duration statistics show a log-normal distribution similar to that obtained under clean conditions when the arc current exceeds the minimum arc sustaining current. At sufficiently high currents arc duration statistics become independent of organic exposure. The envelope of the activated curves is predicted by the activation theory of Gray, Uhrig and Hohnstreiter.