TiO₂ microsphere-based metamaterials exhibiting effective magnetic response in the terahertz regime

Riad Yahiaoui, Mario Maglione, Christelle Kalde, Filip Kaldec, Petr Kužel,
U-Chan Chung, Catherine Elissalde

► To cite this version:

Riad Yahiaoui, Mario Maglione, Christelle Kalde, Filip Kaldec, Petr Kužel, et al.. TiO₂ microsphere-based metamaterials exhibiting effective magnetic response in the terahertz regime. Applied physics. A, Materials science & processing, 2012, 109 (4), pp.891-894. 10.1007/S00339-012-7356-X . hal-00752457

HAL Id: hal-00752457

<https://hal.science/hal-00752457>

Submitted on 6 Dec 2012

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

TiO₂ microsphere-based metamaterials exhibiting effective magnetic response in the terahertz regime

R. Yahiaoui · H. Němec · C. Kadlec · F. Kadlec ·
P. Kužel · U.-C. Chung · C. Elissalde · M. Maglione ·
P. Mounaix

Received: 15 February 2012 / Accepted: 10 October 2012 / Published online: 1 November 2012
© Springer-Verlag Berlin Heidelberg 2012

Abstract Thin layers of all-dielectric metamaterials based on TiO₂ spherical particle resonators are investigated. A new method based on spray drying of dissolved nanoparticles is used in the fabrication process. Spectral footprints of electric and magnetic dipoles are reported numerically and through experimental tests. It is a promising step for the construction of novel three-dimensional isotropic metamaterials exhibiting desired electromagnetic properties for terahertz applications.

1 Introduction

Since their advent, metamaterials have been explored for their potential use in sub-diffraction-limited imaging [1], medical imaging [2], sensing applications [3], cloaking [4], and so on. We focus in this paper on the study of all-dielectric (AD) metamaterials based on layers of titanium dioxide (TiO₂) microspheres. Their effective electric and magnetic responses are related to Mie resonances in each

single particle. For high-enough dielectric permittivity of the particles, it is then possible to achieve e.g. negative effective magnetic permeability [5]. Although AD metamaterials have raised broad interests [6], only a few of them have been experimentally shown to present a magnetic resonance in the THz spectral range. For example, laser micro-machining was employed to fabricate a tunable THz metamaterial made of SrTiO₃ rods [7]. The majority of other works focused on the microwave region. For instance, Zhao et al. demonstrated experimentally a negative magnetic permeability at microwave frequencies in a three-dimensional dielectric composite metamaterial based on high dielectric permittivity cubic particles of Ba_{0.5}Sr_{0.5}TiO₃ (BST) coated with Teflon (PTFE) [8]. Vendik and Gashinova [9] in their work investigated theoretically and numerically a periodic composite medium consisting of two lattices of dielectric spherical particles with different diameters or dielectric constants at microwave frequencies. The authors showed that an effective isotropic double negative medium (DNG) can be realized in the frequency region where the resonance of the TM mode in one kind of particles and of the TE mode in the other kind of particles are achieved simultaneously. Moreover, Peng et al. [10] observed experimentally a left-handed behavior at gigahertz frequencies in an array of standard dielectric resonators. Lepetit et al. [11] have measured a negative refractive index in an all-dielectric metamaterial in the microwave frequency range. Shibuya et al. [12] predicted theoretically a left-handed behavior in a lattice combining two sets of TiO₂ cubes with two different sizes.

2 Our investigated metamaterials

In this work, inexpensive methods were used to fabricate monodisperse micron-sized spheres. First, we mixed com-

R. Yahiaoui (✉) · P. Mounaix
LOMA, Université Bordeaux 1, CNRS, UMR 5798, 33400
Talence, France
e-mail: r.yahiaoui@loma.u-bordeaux1.fr

H. Němec · C. Kadlec · F. Kadlec · P. Kužel
Institute of Physics, Academy of Sciences of the Czech Republic,
Na Slovance 2, 182 21 Prague 8, Czech Republic

U.-C. Chung · C. Elissalde · M. Maglione
ICMCB, Université Bordeaux, CNRS – UPR 9048, 87 Avenue du
Docteur Albert Schweitzer, 33608 Pessac cedex, France

U.-C. Chung
CRPP, CNRS – UPR 8641, 115 Avenue du Docteur Albert
Schweitzer, 33600 Pessac cedex, France

Fig. 1 (a) Schematic view of the simulated microsphere-based metamaterial, with the relevant geometrical dimensions: diameter $d = 45 \mu\text{m}$, period $P = 103 \mu\text{m}$, and the appropriate electric and magnetic field polarizations. (b) Scanning electron microscope images of our TiO_2 microspheres before the sorting procedure

mercial TiO_2 nanoparticles with ethanol to obtain a liquid suspension, which was suddenly dried upon spraying through a flame. This resulted in assembling TiO_2 nanoparticles into fragile mostly spherical dense clusters. These microspheres were then sintered in a tube furnace at 1200°C for 2 h, in order to solidify them and to minimize their porosity. A scanning-electron-microscope image of these particles is shown in Fig. 1b.

The microspheres were finally sieved and sorted along their diameters d . We investigated powders with the following diameters: (i) $\text{MS}_{<38}$, $d < 38 \mu\text{m}$, (ii) MS_{38-40} , $38 \mu\text{m} < d < 40 \mu\text{m}$, and (iii) MS_{40-50} , $40 \mu\text{m} < d < 50 \mu\text{m}$.

3 Result of numerical and experimental characterization

We measured the complex transmission and reflection of the samples by terahertz time domain spectroscopy (THz-TDS) to retrieve the effective electromagnetic response of the metamaterial structures. A thin layer of TiO_2 microparticles has been spread randomly between two thick blocks of sapphire separated by a $70 \mu\text{m}$ thick Teflon o-ring. This fixes and controls the thickness of the film, which is then essentially composed of a single layer of the microparticles.

THz pulses passing through the structure directly carry information about the complex transmittance of the powder, while THz pulses coming from internal reflections in the blocks and from the partial reflection on the sapphire/powder interface carry information also about the complex reflectance of the powder (Fig. 2a). These pulses are resolved as a sequence of echoes in the time-domain signal transmitted through the entire structure [13] (see Fig. 2b). The sapphire block B is about two times thicker than the block A, which ensures that the first internal reflection in the block A does not mix with the internal reflections

Fig. 2 (a) Scheme of the pulse propagation through the structure AXB (sapphire–powder–sapphire) and within the three associated reference measurements. The reflected beams are shifted vertically for graphical clarity. (b) Example of the time-domain signal transmitted through the structure AXB. Dotted lines delimit the intervals containing: I—main pulse (E_{0-AXB}); II—1st echo in A (E_{1-AXB}); III—superposition of 1st echo in B and 2nd echo in A

from the block B. The measurement has to be supplemented by three reference measurements: (i) waveform transmitted through the block A (including the first echo), (ii) waveform transmitted through the block B, and (iii) waveform transmitted through an empty space. The complex transmittance and reflectance spectra of the metamaterial are then calculated from

$$t = \frac{E_0^{AXB} E^{\text{ref}}}{E_0^A E_0^B} \cdot \frac{4z_B}{(1+z_A)(1+z_B)}, \quad (1)$$

$$r = \frac{E_1^{AXB} E_0^A}{E_1^A E_0^{AXB}} \cdot \frac{1-z_A}{1+z_A}, \quad (2)$$

where z_A and z_B are the relative wave impedances of the blocks A and B, respectively, and E denotes the Fourier transformations (spectra) of the time-domain signals defined in Fig. 2a. The use of the same blocks in the reference measurements ensures that the transmittance and reflectance phase is not corrupted by a possible uncertainty in the determination of the thickness of these blocks. We used thick sapphire blocks (3 and 6 mm). The internally reflected pulses (echoes) are thus separated by more than 60 ps (see dotted lines in Fig. 2b), which enables a good spectral resolution ($1/(60 \text{ ps}) \approx 0.03 \text{ THz}$). The transmission and reflection spectra are then extracted numerically as shown in Fig. 3. In the related numerical simulations, we considered a periodic array of monodisperse spheres ($d = 45 \mu\text{m}$, filling factor =

Fig. 3 Spectra of the sample MS₄₀₋₅₀: simulated (solid lines) and measured (hollow circles) magnitude of the reflection (a), phase of the reflection (b), magnitude of the transmission (c), phase of the transmission (d)

10 %), as illustrated in Fig. 1a. We found that TiO₂ microparticles have a relative dielectric permittivity of about 92 and a moderate loss level of about 5 % ($\tan \delta \sim 0.05$) at terahertz frequencies. The overall agreement between simulation and experiment is rather good, keeping in mind that a regular structure is simulated while the measured sample is necessarily irregular and the microspheres may touch each other. We notice minor differences in the simulated phases compared to the measured ones (cf. Fig. 3b and d) above the first Mie mode around 0.75 THz, which is probably due to the polydispersity of the microspheres.

4 Retrieval of the effective electromagnetic parameters

Using the retrieval method based on the inversion of Fresnel equations [14], we determined the effective permittivity and permeability. The result of the extraction procedure is given in Fig. 4. There is a good agreement between the simulated and the measured effective magnetic responses (Fig. 4b). We believe that magnetic resonances are excited individually within each particle forming the metamaterial and they are only weakly influenced by the mutual coupling between particles [7, 16, 17]. Both measured and calculated effective dielectric permittivities are rather low (Fig. 4a), which is due to the low filling factor (about 10 %) and low percolation degree which is controlled by the actual structure of the film [15].

Furthermore, the calculated permittivity at low frequencies is significantly lower than the measured one and the resonance observed here is not as strong as the measured one. This difference between simulation and experiment can be

partly explained by the complex topology of our samples (note that a simple square lattice of microspheres was considered in the simulations represented in Fig. 1a). In order to attempt reproducing the resonant behavior of the electric response, we performed further numerical calculations taking into account pairs of microspheres in contact (dimers) arranged in a rectangular lattice, as illustrated in Fig. 4c. The resonant behavior, similar to the experimental one shown in Fig. 4d, is then observed in the permittivity spectra for a probing electric field parallel to the dimer axis.

On the one hand, polydispersity of the spheres in samples broadens the resonance and prevents μ from reaching negative values. On the other hand, numerical simulations show that using a much larger filling fraction (e.g. 50 %) provides a metamaterial with $\mu < 0$ in spite of the inhomogeneous broadening. This implies that the microparticles fabricated by our method can induce a negative-permeability metamaterial for large filling fractions. Unfortunately, the high absorption for filling fractions exceeding ~ 15 % precluded an accurate experimental determination of the permeability in such structures.

5 Conclusions

In conclusion, TiO₂ microparticle-based metamaterials were fabricated using an inexpensive spray-drying method. Numerical calculations and experimental characterizations have been conducted, demonstrating effective electric and magnetic response at terahertz frequencies, due to Mie resonances. It is a promising step for implementing improved electromagnetic functionalities, involving cheap and easily made metamaterials.

Fig. 4 Dielectric permittivity (a) and magnetic permeability (b) of the sample MS₄₀₋₅₀. Circles: measured data, lines: simulations incorporating inhomogeneous broadening. (c) Configuration of the dimer, with the probing electric field parallel to its axis. (d) Real part of the dielectric permittivity of the dimer (sphere diameter 50 μm, filling factor 15 %) compared to the experimental permittivity from (a)

Acknowledgements The work at the University of Bordeaux 1 was supported by the project 'GIS-AMA-SAMM'. Financial support by the Czech Science Foundation (Project No. P204/12/0232) is also acknowledged.

References

1. N. Fang, H. Lee, C. Sun, X. Zhang, *Science* **308**, 534 (2005)
2. M.J. Freire, R. Marques, L. Jelinek, *Appl. Phys. Lett.* **93**, 231108 (2008)
3. K. Kneipp, H. Kneipp, I. Itzkan, R.R. Dasari, M.S. Feld, *J. Phys. Condens. Matter* **14**, 597 (2002)
4. D. Schurig, J.J. Mock, B.J. Justice, S.A. Cummer, J.B. Pendry, A.F. Starr, D.R. Smith, *Science* **314**, 977 (2006)
5. S. O'Brien, J.B. Pendry, *J. Phys. Condens. Matter* **14**, 4035 (2002)
6. Q. Zhao, J. Zhou, F. Zhang, D. Lippens, *Mater. Today* **12**, 60 (2009)
7. H. Němec, P. Kužel, F. Kadlec, C. Kadlec, R. Yahiaoui, P. Mounaix, *Phys. Rev. B* **79**, 241108 (2009)
8. Q. Zhao, L. Kang, B. Du, H. Zhao, Q. Xie, X. Huang, B. Li, J. Zhou, L. Li, *Phys. Rev. Lett.* **101**, 027402 (2008)
9. O.G. Vendik, M.S. Gashinova, Artificial double negative (DNG) media composed by two different dielectric sphere lattices embedded in a dielectric matrix, in *Proc. 34th Eur. Microwave Conf.*, Amsterdam (2004), pp. 1209–1212
10. L. Peng, L. Ran, H. Chen, H. Zhang, J.A. Kong, M.T. Grzegorzczak, *Phys. Rev. Lett.* **98**, 157403 (2007)
11. T. Lepetit, E. Akmonsoy, J.-P. Ganne, *Appl. Phys. Lett.* **95**, 121101 (2009)
12. K. Shibuya, K. Takano, N. Matsumoto, K. Izumi, H. Miyazaki, Y. Jimba, M. Hangyo, Terahertz metamaterials composed of TiO₂ cube arrays, in *Proc. Metamaterials*, Pamplona (2008), pp. 777–779
13. L. Duvillaret, F. Garet, J.-L. Coutaz, *Appl. Opt.* **38**, 409 (1999)
14. D.R. Smith, S. Schultz, P. Markoš, C.M. Soukoulis, *Phys. Rev. B* **65**, 195104 (2002)
15. H. Němec, Z. Mics, M. Kempa, P. Kužel, O. Hayden, Y. Liu, T. Bein, D. Fattakhova-Rohlfing, *J. Phys. Chem. C* **115**, 6968 (2011)
16. H. Němec, C. Kadlec, F. Kadlec, P. Kužel, R. Yahiaoui, U.-C. Chung, C. Elissalde, M. Maglione, P. Mounaix, *Appl. Phys. Lett.* **100**, 061117 (2012)
17. R. Yahiaoui, H. Němec, P. Kužel, F. Kadlec, C. Kadlec, P. Mounaix, *Opt. Lett.* **34**, 3541 (2009)