

Convergence analysis of the Bøl-Reese discrete model for rubber

Roberto Alicandro, Marco Cicalese, Antoine Gloria

► **To cite this version:**

Roberto Alicandro, Marco Cicalese, Antoine Gloria. Convergence analysis of the Bøl-Reese discrete model for rubber. Continuum Models and Discrete Systems CMDS 11, Jul 2007, Paris, France. 2008, Mines Paris ParisTech. <inria-00166846v4>

HAL Id: inria-00166846

<https://hal.inria.fr/inria-00166846v4>

Submitted on 23 Oct 2007

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



INSTITUT NATIONAL DE RECHERCHE EN INFORMATIQUE ET EN AUTOMATIQUE

*Convergence analysis of the Bül-Reese discrete
model for rubber*

R. Alicandro¹, M. Cicalese², A. Gloria³

N° 6270

August, 2007

Thème NUM



*R*apport
de recherche



Convergence analysis of the Bül-Reese discrete model for rubber

R. Alicandro¹, M. Cicalese², A. Gloria³ *

Thème NUM — Systèmes numériques
Projet MICMAC

Rapport de recherche n° 6270 — August, 2007 — 9 pages

Abstract: In [1], Bül and Reese have introduced a discrete model for polymer networks by means of a finite element modeling. In [2, 3], they present details on the method and a comparison with real experiments. A key parameter of their model is the size h of the finite element mesh, that is meant to be small in practice. The aim of the present work is to study the asymptotic behaviour (and the convergence of the finite element method) when the meshsize goes to zero. In particular, we address the properties satisfied by the model at the limit, depending on the properties of the mesh.

Key-words: nonlinear elasticity, rubber, discrete system, finite element method

* ¹ DAEIMI, Università di Cassino, via Di Biasio 43, 03043 Cassino (FR), Italy ; ² Dipartimento di Matematica e Applicazioni 'R. Caccioppoli', Università di Napoli, via Cintia, 80126 Napoli, Italy ; ³ CER-MICS - ENPC & INRIA Paris-Rocquencourt, 6 et 8 avenue Blaise Pascal - Champs sur Marne, France ; Contact: alicandr@unicas.it, cicalese@unina.it, antoine.gloria@inria.fr

Propriétés de convergence du modèle discret de Böl-Reese pour le caoutchouc

Résumé : Dans [1], Böl et Reese ont introduit un modèle discret de réseau de polymères par éléments finis. Dans [2, 3], les auteurs détaillent leur méthode et comparent les résultats numériques obtenus à des expériences réelles. Un des paramètres clés de leur modèle est la taille du pas h du maillage, qui est petit en pratique. L'objectif de ce travail est d'étudier le comportement asymptotique (ainsi que la convergence de la méthode des éléments finis) lorsque h tend vers zéro. En particulier, nous étudions les propriétés satisfaites par le modèle à la limite, en fonction, des propriétés du maillage.

Mots-clés : élasticité non linéaire, caoutchouc, système discret, méthode des éléments finis

Phenomenological constitutive laws for rubber-like materials often involve parameters which lack of physical motivation. In addition, they are usually difficult to fit in practice. Much attention has been paid in the recent years to microscopically-based models. This kind of models aims at pointing out the microscopic features that govern the macroscopic behavior of the material, such as the geometry of the underlying polymer network. Such a model has been introduced by BöL and Reese in [1]. In addition to the physical parameters provided by physics at the scale of the polymer chains (such as the free energy of a chain), this model involves two geometric parameters: a typical distance $h > 0$ (which is meant to be small) and a tetraedral mesh.

The aim of the present work is to study the asymptotic properties of the model when h goes to zero for different assumptions on the mesh.

This note is organized as follows:

Contents

| | | |
|----------|---------------------------------------|----------|
| 1 | The BöL-Reese model | 4 |
| 1.1 | The geometry | 4 |
| 1.2 | The energy | 4 |
| 2 | Convergence analysis | 5 |
| 2.1 | Assumptions on the energies | 5 |
| 2.2 | The periodic case | 6 |
| 2.3 | The stochastic case | 7 |
| 3 | Conclusion | 8 |

1 The BöL-Reese model

1.1 The geometry

For the sake of simplicity, let Ω denote the unit cube of \mathbb{R}^3 and \mathcal{T}_h be a tetrahedral mesh of Ω . The typical distance we associate with the mesh is defined as follows:

$$h = \sqrt[3]{\frac{1}{N_{\text{el}}}},$$

where N_{el} denotes the number of elements (tetraedras) of \mathcal{T}_h .

From a modeling point of view, each edge of the mesh represents an elastic spring with an energy related to the underlying polymer network.

Let d be a displacement field of the mesh defined at each vertex x_i of \mathcal{T}_h by d_i . One can associate with d a continuous displacement field on Ω as follows: v_h is the unique piecewise affine function on \mathcal{T}_h such that for each vertex x_i of \mathcal{T}_h , $v_h(x_i) = x_i + d_i$.

The energy of the system deformed by v_h is then given by

$$E_h(v_h) = \sum_{T \in \mathcal{T}_h} h^3 \sum_{(x_i, x_j) \in T} f_{ij}^T W_{ij}^T \left(\frac{|v_h(x_i) - v_h(x_j)|}{|x_i - x_j|} \right) + \int_{\Omega} W_{\text{vol}}(\nabla v_h), \quad (1)$$

where T denotes elements of \mathcal{T}_h , (x_i, x_j) are distinct pairs of vertices in the tetraedra T , W_{ij}^T is a pair potential, f_{ij}^T is a scaling factor and W_{vol} is an energy density accounting for volume changes of the deformed system.

Let us now describe the pair-potential energy.

1.2 The energy

The energy of the elastic springs is related to the energy of a polymer chain as follows:

$$W_{ij}^T(r) = \frac{k}{\beta} n_{ij}^T \left(\frac{r}{\sqrt{n_{ij}^T}} \mathcal{L}^{-1} \left(\frac{r}{\sqrt{n_{ij}^T}} \right) + \ln \frac{\mathcal{L}^{-1} \left(\frac{r}{\sqrt{n_{ij}^T}} \right)}{\sinh \mathcal{L}^{-1} \left(\frac{r}{\sqrt{n_{ij}^T}} \right)} \right) - \frac{c}{\beta}, \quad (2)$$

where β is the inverse of the absolute temperature, \mathcal{L}^{-1} is the inverse of the Langevin function, k and c are constants and n_{ij}^T is a typical number of segments of a polymer chain. W_{ij}^T can be interpreted as the free energy of a polymer chain made of n_{ij}^T segments at the length $\sqrt{n_{ij}^T} l$, where l denotes the length of a segment.

The factor f_{ij}^T is a measure of the number of polymer chains per unit of volume. We will typically consider it as constant on Ω .

Finally, the energy accounting for volume changes is given by

$$W_{vol}(\xi) = \frac{K}{4}(J^2 - 1 - \ln J), \quad (3)$$

where $K > 0$, ξ is a deformation gradient and $J = \det(\xi)$. The physical origin of this contribution is the Van der Waals forces, which prevent atoms from being too close to one another. The scale of this forces is far larger than the scale of the polymer network, which explains why this contribution is already coarse-grained and somewhat uncorrelated with the description of the network.

In the following section, we study the convergence when $h \rightarrow 0$ of the sequence of minimization problems

$$\inf \{E_h(v_h), v_h \in V_h + BC\},$$

where V_h denotes the space of piecewise affine functions on \mathcal{T}_h and BC stands for the boundary conditions (let say mixed imposed displacement and free traction for instance). In particular, we address both the convergence of the infimum of the energy and the convergence of the minimizers (the deformation field) when $h \rightarrow 0$. This convergence analysis is performed using Γ -convergence (see [4, 5] e.g.).

2 Convergence analysis

2.1 Assumptions on the energies

For technical reasons, in what follows, we will assume that:

- W_{ij}^T satisfies the following standard growth condition of order $p > 1$ for all T and ij : there exist $C \geq c > 0$ such that for all r ,

$$c|r|^p - 1 \leq W_{ij}^T(r) \leq C(|r|^p + 1), \quad (4)$$

- W_{vol} satisfies (4) from above.

In particular, one cannot directly deal with the inverse of the Langevin function. To satisfy the growth condition (4), one may use a truncated series expansion of \mathcal{L}^{-1} , as it is done in [1, 2, 3]:

$$\mathcal{L}^{-1}(\rho) = 3\rho + \frac{9}{5}\rho^3 + \frac{297}{175}\rho^5 + \frac{1539}{875}\rho^7 + O(\rho^9).$$

Replacing \mathcal{L}^{-1} by its development up to order 7 in (2), we obtain a free energy density for a polymer chain which satisfies (4) for $p = 8$.

The energy density W_{vol} given by (3) does not satisfy (4) since $\lim_{\det(\xi) \rightarrow 0} W_{vol}(\xi) = +\infty$ while $\det(\xi) \rightarrow 0$ does not imply $|\xi| \rightarrow \infty$. One possible solution consists in taking a cut-off,

which amounts to relaxing the constraint of incompressibility. A typical cut-off reads as follows:

$$W_{vol}^\eta(\xi) = \begin{cases} W_{vol}(\xi) & \text{if } \det(\xi) > \eta \\ \frac{K}{4}(\eta^2 - 1 - \ln \eta) & \text{otherwise.} \end{cases} \quad (5)$$

For $\eta > 0$ fixed, W_{vol}^η satisfies (4) for C_η large enough. To recover the incompressibility behavior, one can first perform the convergence analysis on the discrete to continuum process for $\eta > 0$ and then let η go to zero at the continuum level. We refer the reader to [6, 7] for technical details.

We are now in position to state our convergence results.

2.2 The periodic case

In this paragraph, we address the convergence of the Bøl-Reese model in the periodic case. To this end, let us assume that the edges of \mathcal{T}_h are obtained by the periodic replication of a unit cell of edges (up to border effects on the boundary), as illustrated in two dimensions on Figure 1.




Figure 1: Two-dimensional periodic mesh, the unit cell is in bold

Let us further assume that the energy of the elastic springs does not depend of the unit cell and on the mesh lengthscale h . As a particular case, one can take n_{ij}^T to be constant on \mathcal{T}_h , as it is done in [1, 2, 3]. Then, [8, Theorem 4.1] shows there exists an homogeneous quasiconvex energy density W_{hom} , which is frame-invariant and satisfies a growth condition of order p , such that:

- $\liminf_{h \rightarrow 0} \{E_h(v_h), v_h \in V_h + BC\} = \inf \{E_{hom}(v), v \in V + BC\}$, where V is the Sobolev space $W^{1,p}(\Omega)$, and

$$E_{hom}(v) = \int_{\Omega} W_{hom}(\nabla v);$$

- W_{hom} is given by the asymptotic discrete homogenization formula

$$W_{hom}(\xi) = \liminf_{h \rightarrow 0} \{E_h(v_h), v_h \in V_h, v(x_i) = \xi \cdot x_i \text{ if } d(x_i, \partial\Omega) \leq 2h\}.$$

In addition, minimizers u_h of E_h on $V_h + BC$ weakly converge in $W^{1,p}(\Omega)$ to minimizers u_{hom} of E_{hom} on $V + BC$. This proves in particular the convergence of the solutions of the finite element modelling of rubber introduced by Böl and Reese.

In the periodic case, the energy density at the limit is frame-invariant. However it is not isotropic in general. To ensure the isotropy, one may use a stochastic framework. The end of this paragraph is dedicated to the study of a simple example for which the energy density at the limit is not isotropic.

Let us consider simple linear springs by setting

$$W_{ij}^T(v_h) = K \left(\frac{|v_h(x_i) - v_h(x_j)|}{|x_i - x_j|} \right)^2 \quad \text{and} \quad W_{vol} = 0$$

on the mesh sketched on Figure 1. Then, recalling [8, Remark 5.2], the homogenized energy density is quadratic and we end up with a convex minimization problem on one single periodic cell. The infimum is trivial and shows that the homogenized energy is not isotropic. It is actually enough to see that the material is stiffer in the direction $e_2 - e_1$ than in the direction $e_1 + e_2$ (where e_1 and e_2 denote the canonical basis of \mathbb{R}^2).

2.3 The stochastic case

Let us quickly recall the concept of admissible stochastic network on a probability space (Ξ, \mathcal{F}, P) used in [9, 7], which is a particular case of the stochastic networks introduced by Blanc, Le Bris and Lions in [10, 11].

Let $\Lambda = \{y_i\}_{i \in \mathbb{Z}^d} \in (\mathbb{R}^d)^{\mathbb{Z}^d}$ be a set of points. We say that Λ is an admissible set of points if it satisfies the two following conditions:

- i. there exists $R > 0$ such that $\#\Lambda \cap B(y, R) > 0$ for all $y \in \mathbb{R}^d$;
- ii. there exists $r > 0$ such that $d(y_i, \Lambda \setminus \{y_i\}) \geq r$ for all $i \in \mathbb{Z}^d$.

In particular, to each admissible set of points Λ one can associate a Delaunay triangulation $\mathcal{D}(\Lambda)$. A stochastic lattice $\mathcal{L} : \Xi \rightarrow (\mathbb{R}^d)^{\mathbb{Z}^d}$ is said to be admissible, if for P -almost every $\omega \in \Xi$, $\mathcal{L}(\omega)$ is an admissible set of points, and if the Delaunay triangulation is regular in the sense of the interpolation theory.

Given a realization $\Lambda(\omega)$ of a stochastic lattice, one may rescale the lattice by a factor h , setting $y_i^h(\omega) = hy_i(\omega)$. Let us then define $\Lambda(\omega)^h(\Omega) = \{y_i^h \in \mathbb{R}^3, y_i \in \Lambda(\omega) \text{ and } y_i^h \in \Omega\}$, which is the intersection of the rescaled lattice with Ω . Using the notations of Böl and Reese, one may think of a mesh \mathcal{T}_h as the Delaunay triangulation of $\Lambda(\omega)^h(\Omega)$.

In what follows, we assume that \mathcal{T}_h is related to a stochastic network in the way described above and we add an index ω to make the stochastic dependence more explicit. Furthermore we will make some hypotheses related to the stochastic network and the probability space:

- (a) there exists a stationary translation group that acts on the stochastic lattice and which is ergodic for P ;
- (b) there exists a stationary group of rotations that acts on the stochastic lattice (the stochastic lattice is then said to be rotation invariant on average).

Roughly speaking, the translation invariance allows us to obtain a deterministic limit whereas the invariance by rotation implies that the energy density at the limit is isotropic. We refer the interested reader to [7] for the precise formulation of the assumptions and the proofs of the following result.

Within hypothesis (a), there exists an homogeneous quasiconvex energy density W_{hom} , which is frame-invariant and satisfies a growth condition of order p , such that:

- For almost all $\omega \in \Xi$,

$$\liminf_{h \rightarrow 0} \{E_h^\omega(v_h^\omega), v_h^\omega \in V_h^\omega + BC\} = \inf \{E_{hom}(v), v \in V + BC\},$$

where V is the Sobolev space $W^{1,p}(\Omega)$, and

$$E_{hom}(v) = \int_{\Omega} W_{hom}(\nabla v);$$

- W_{hom} is given by the asymptotic discrete homogenization formula

$$W_{hom}(\xi) = \lim_{h \rightarrow 0} \int_{\Xi} \inf \{E_h^\omega(v_h^\omega), v_h^\omega \in V_h^\omega, v(x_i) = \xi \cdot x_i \\ \text{if } d(x_i, \partial\Omega) \leq 2hR\} dP(\omega).$$

In addition, minimizers u_h^ω of E_h^ω on $V_h^\omega + BC$ weakly converge in $W^{1,p}(\Omega)$ to minimizers u_{hom} of E_{hom} on $V + BC$. This proves in particular the convergence of the solutions of the finite element modelling of rubber introduced by Böl and Reese.

In addition, if (b) holds, the stochastic network is rotation invariant on average, and W_{hom} is isotropic.

3 Conclusion

In the first section, we have recalled the finite element modelling of rubber developed by Böl and Reese and we have pointed out some convergence issues related to their formulation. In the following sections, we have analyzed the asymptotic behaviour of the model. In particular, we have identified two cases for which their model provides a finite element approximation of an underlying continuous model. The continuous models obtained both satisfy the frame invariance property and the usual incompressibility behaviour used for rubber modelling (up to some technicalities detailed in [7]). However, only the stochastic model is ensured to yield an isotropic energy density at the limit. We have also provided a periodic example which is not isotropic at the limit.

References

- [1] M. Böl and S. Reese. Finite element modelling of polymer networks based on chain statistics. In J. Busfield and A. Muhr, editors, *Constitutive models for rubber III (Proceedings of the third European conference on constitutive models for rubber)*, pages 203–211, Lisse, 2003. A.A. Balkema.
- [2] M. Böl and S. Reese. Finite element modelling of rubber-like polymers based on chain statistics. *Int. J. Sol. Struc.*, 43:2–26, 2006.
- [3] M. Böl and S. Reese. Finite element modelling of rubber-like materials - a comparison between simulation and experiment. *Journal of Materials Sc.*, 40:5933–5939, 2005.
- [4] A. Braides. Γ -convergence for beginners, volume 22 of *Oxford Lecture Series in Mathematics and Its Applications*. Oxford University Press, 2002.
- [5] A. Braides. A handbook of Γ -convergence. volume 3 of *Handbook of Differential Equations: Stationary Partial Differential Equations*, pages 101–213. Elsevier, Amsterdam, 2006.
- [6] A. Gloria. *Méthodes numériques et modélisation multiéchelle en élasticité non linéaire*. PhD thesis, ENPC, 2007.
- [7] R. Alicandro, M. Cicalese, and A. Gloria. Integral representation results for energies defined on stochastic lattices and application to nonlinear elasticity. In preparation.
- [8] R. Alicandro and M. Cicalese. A general integral representation result for the continuum limits of discrete energies with superlinear growth. *SIAM J. Math. Anal.*, 36(1):1–37, 2004.
- [9] R. Alicandro, M. Cicalese, and A. Gloria. Mathematical derivation of a rubber-like stored energy functional. Submitted.
- [10] X. Blanc, C. Le Bris, and P.L. Lions. Du discret au continu pour des réseaux aléatoires d’atomes. *C. R. Acad. Sci. Paris, Série I*, 342:627–633, 2006.
- [11] X. Blanc, C. Le Bris, and P.L. Lions. The energy of some microscopic stochastic lattices. *Arch. Rational Mech. Anal.*, to appear.



Unité de recherche INRIA Rocquencourt
Domaine de Voluceau - Rocquencourt - BP 105 - 78153 Le Chesnay Cedex (France)

Unité de recherche INRIA Futurs : Parc Club Orsay Université - ZAC des Vignes
4, rue Jacques Monod - 91893 ORSAY Cedex (France)

Unité de recherche INRIA Lorraine : LORIA, Technopôle de Nancy-Brabois - Campus scientifique
615, rue du Jardin Botanique - BP 101 - 54602 Villers-lès-Nancy Cedex (France)

Unité de recherche INRIA Rennes : IRISA, Campus universitaire de Beaulieu - 35042 Rennes Cedex (France)

Unité de recherche INRIA Rhône-Alpes : 655, avenue de l'Europe - 38334 Montbonnot Saint-Ismier (France)

Unité de recherche INRIA Sophia Antipolis : 2004, route des Lucioles - BP 93 - 06902 Sophia Antipolis Cedex (France)

Éditeur
INRIA - Domaine de Voluceau - Rocquencourt, BP 105 - 78153 Le Chesnay Cedex (France)
<http://www.inria.fr>
ISSN 0249-6399